


Main Characteristics

- Heat-sealable on non-metallized side from 105°C;
- Medium water vapor barrier;
- Optimum light barrier;
- Optimum performance in horizontal and vertical form-fill-seal packing machines.

Typical Applications

- Flexible packaging for food: cookies, snacks, chocolate bars, ice cream, cereal bars;
- Non-food flexible packaging: decorative applications in general;
- Continuous labels (WAL Roll Fed), monolayers or laminate;
- Developed for HFFS - Horizontal Form Fill Seal and VFFS - Vertical Form Fill Seal filling processes.



Properties	Methodology	Unit	Range	17TMZ	20TMZ
Physical Properties					
Nominal Thickness	DIN 53370	µm	Target	17.0	20.0
			Min.	16.2	19.0
			Max.	17.9	21.0
		Gauge	Target	66.9	78.7
			Min.	63.6	74.8
			Max.	70.3	82.7
Unit Weight	ASTM D 4321	g/m ²	Target	15.4	18.1
			Min.	14.6	17.2
			Max.	16.2	19.0
		lb/ream	Target	9.5	11.1
			Min.	9.0	10.6
			Max.	9.9	11.7
Yield	ASTM D 4321	m ² /kg	Target	65.0	55.2
			Min.	61.9	52.6
			Max.	68.4	58.2
		in ² /lb	Target	45698	38844
			Min.	43522	36994
			Max.	48104	40888
Surface Treatment	ASTM D 2578	dinas/cm	Target	NA	
			Min.	NA	
Coefficient of Friction	NT	ASTM D 1894	-	Target	0.25
				Min.	0.20
				Max.	0.35
Optical Properties					
Optical Density	-	%	Target	≥ 2,0	
Mechanical Properties					
Tensile Strength	MD	ASTM D 882	N/mm ²	Target	140
	TD			240	
	MD		lbf/in ²	Target	20305
	TD			34809	
Elongation at Break	MD	ASTM D 882	%	Target	170 185
	TD			40	
Shrinkage	MD	ASTM D 1204	%	Target	3
	TD			1	
Sealing Range	NT	ASTM F 88	°C	Target	105 - 130
			°F	Target	221 - 266
Sealing Strength	NT	ASTM F 88	g/25mm or gf/in	Target	400 450
				Min.	300
Barrier Properties					
TPVA 38°C / 90%UR	ASTM F 1249	g H ₂ O / (m ² .dia)	Target	≤ 0.8	
WVTR 100°F / 90%RH	ASTM F 1249	g H ₂ O / (100in ² .day)	Target	≤ 0.05	
TPO ₂ 23°C / 0%UR	ASTM D 3985	cm ³ O ₂ / (m ² .dia)	Target	≤ 153	
OTR 73°F / 0%RH	ASTM D 3985	cm ³ O ₂ / (100in ² .day)	Target	≤ 8.4	

1. Acronyms:
MD: Machine Direction | TD: Transverse Direction;
NT: Non Treated Layer | T: Treated Layer;
WAL: Wrap Around Label.

2. Additional:
The restrained information in this datasheet represent typical data, and does not constitute genuine warranty liability as far as the product process and or application. In case of doubts or development of other thicknesses or applications, consult your dealer or send e-mail to: contato@polofilms.com.br.

Notes:

The use of metallized films in the conversion process is recommended within a maximum period of 2 months from the billing date, in order to minimize the risk of loss of integrity of the metal layer and damage to the barrier properties. Climatic conditions have a very relevant influence on the surface energy of the metallized face. Therefore, we recommend the application of primer or corona treatment on the metallized face before printing or laminating with another substrate.

Food Contact Regulations

METAL Family films comply with Mercosul, ANVISA, FDA (Food and Drug Administration) and the European Community legislations for applications involving direct contact with food. Full details are provided in the Declaration of Conformity. Customers intending to use METAL Family films for applications intended to come into contact with food should request a copy of that document from POLO Films. The MSDS (Material Safety Data Sheet), as well as the evaluation of conformity for contact with food from other legislations are also available upon request. Contact your dealer for any questions.

Storage and Transportation Terms & Conditions

All products are stored and transported in dry, covered and clean environments. It is recommended that storage and transportation take place at temperature around 30°C and 60% relative humidity.

If the temperature and humidity are not as recommended, the following issues may occur:

- Decreased level of surface treatment, leading to printing and/or lamination difficulties;
- Decreased film transparency;
- Too low CoF, making processing and machinability difficult.

BOPP films are recommended to be kept at operating room temperature for 24 hours before use.

Dimensional Specifications / Product Validity

Width	Minimum: 0 mm Maximum: 2 mm (from standard width)
Outer Diameter*	Minimum: 30 mm Maximum: 20 mm (from standard diameter)
Core	Minimum: 1 mm Maximum: 1 mm (from standard diameter)
Splices per roll	Maximum: 2
% of Splices per order	Maximum: 30%
Shelf Life (after production)	6 months

* For other dimensional information, consult your dealer.

Polo Films Nomenclature

Unit Weight or Thickness Technology Main Feature Sealing Treatment

20 TMZ 10

Unit Weight/ Thickness

Expressed in g/m². Used for white/opaque films;
Expressed in µm. Used for transparent, matte and metallized films.

Technology

T - Tenter | C - Cast | P - BOPET.

Main Feature

MZ - Heat-sealable metallized for printing and/or lamination.

Specialty

Not applicable.

Sealing

0 - Not Sealable;
1 - Sealing on the Inner Face;
2 - Sealing on the Outer Face;
3 - Sealing on both Sides.

Treatment

0 - No Treatment;
1 - Treatment on Inner Face;
2 - Treatment on Outer Face;
3 - Treatment on both Sides.