


Main Characteristics

- Both sides heat-sealable, non-treated side from 105°C;
- Surface treatment on inner or outer layer;
- Optimum optical properties (gloss and transparency);
- CoF with controlled slipping properties and stable at higher temperature than room temperature (Stable Hot Slip);
- Excellent performance in portfolio-type packing machines.

Typical Applications

- Flexible packaging for food: cookies, snacks, instant noodle and product grouping packaging;
- Non-food flexible packaging: monolayers or laminate;
- Developed for HFFS - Horizontal Form Fill Seal and VFFS - Vertical Form Fill Seal filling processes.



Properties	Methodology	Unit	Range	17TSYCMS	
Physical Properties					
Nominal Thickness	DIN 53370	µm	Target	17.0	
			Min.	16.2	
			Max.	17.9	
		Gauge	Target	66.9	
			Min.	63.6	
			Max.	70.3	
Unit Weight	ASTM D 4321	g/m²	Target	15.4	
			Min.	14.6	
			Max.	16.2	
		lb/ream	Target	9.5	
			Min.	9.0	
			Max.	9.9	
Yield	ASTM D 4321	m²/kg	Target	65.0	
			Min.	61.9	
			Max.	68.4	
		in²/lb	Target	45698	
			Min.	43522	
			Max.	48104	
Surface Treatment	T	ASTM D 2578	dinas/cm	Target	42
				Min.	38
Coefficient of Friction	NT	ASTM D 1894	-	Target	0.25
				Min.	0.22
				Max.	0.28
Optical Properties					
Haze	ASTM D 1003	%	Target	1.6	
			Max.	3.0	
Gloss (45°)	ASTM D 2457	u.b.	Target	95	
			Min.	85	
Mechanical Properties					
Tensile Strength	MD	ASTM D 882	N/mm²	Target	140
	TD			250	
	MD		lbf/in²	Target	20305
	TD			36260	
Elongation at Break	MD	ASTM D 882	%	Target	180
	TD			45	
Shrinkage	MD	ASTM D 1204	%	Target	3
	TD			1	
Sealing Range	NT	ASTM F 88	°C	Target	105 - 130
			°F	Target	221 - 266
Sealing Strength	NT	ASTM F 88	g/25mm or gf/in	Target	400
				Min.	300
Barrier Properties					
TPVA 38°C / 90%UR	ASTM F 1249	g H ₂ O / (m².dia)	Target	≤ 10	
WVTR 100°F / 90%RH	ASTM F 1249	g H ₂ O / (100in².day)	Target	≤ 0.64	
TPO ₂ 23°C / 0%UR	ASTM D 3985	cm³ O ₂ / (m².dia)	Target	≤ 3800	
OTR 73°F / 0%RH	ASTM D 3985	cm³ O ₂ / (100in².day)	Target	≤ 244	

1. Acronyms:

MD: Machine Direction | TD: Transverse Direction;
NT: Non Treated Layer | T: Treated Layer.

2. Additional:

The restrained information in this datasheet represent typical data, and does not constitute genuine warranty liability as far as the product process and or application. In case of doubts or development of other thicknesses or applications, consult your dealer or send e-mail to: contato@polofilms.com.br.



Food Contact Regulations

SEAL Family films comply with Mercosul, ANVISA, FDA (Food and Drug Administration) and the European Community legislations for applications involving direct contact with food. Full details are provided in the Declaration of Conformity. Customers intending to use SEAL Family films for applications intended to come into contact with food should request a copy of that document from POLO Films. The MSDS (Material Safety Data Sheet), as well as the evaluation of conformity for contact with food from other legislations are also available upon request. Contact your dealer for any questions.

Storage and Transportation Terms & Conditions

All products are stored and transported in dry, covered and clean environments. It is recommended that storage and transportation take place at temperature around 30°C and 60% relative humidity.

If the temperature and humidity are not as recommended, the following issues may occur:

- Decreased level of surface treatment, leading to printing and/or lamination difficulties;
- Decreased film transparency;
- Too low CoF, making processing and machinability difficult.

BOPP films are recommended to be kept at operating room temperature for 24 hours before use.

Dimensional Specifications / Product Validity

Width	Minimum: 0 mm Maximum: 2 mm (from standard width)
Outer Diameter*	Minimum: 30 mm Maximum: 20 mm (from standard diameter)
Core	Minimum: 1 mm Maximum: 1 mm (from standard diameter)
Splices per roll	Maximum: 2
% of Splices per order	Maximum: 30%
Shelf Life (after production)	6 months

* For other dimensional information, consult your dealer.

Polo Films Nomenclature

Unit Weight or Thickness Technology Main Feature Specialty Sealing Treatment

17 TSY CMS 32

Unit Weight/ Thickness

Expressed in g/m². Used for white/opaque films;
Expressed in µm. Used for transparent, matte and metallized films.

Technology

T - Tenter | C - Cast.

Main Feature

SY - Transparent heat-sealable for printing and/or lamination.

Specialty

CMS - Stable slip at high temperatures.

Sealing

0 - Not Sealable;
1 - Sealing on the Inner Face;
2 - Sealing on the Outer Face;
3 - Sealing on both Sides.

Treatment

0 - No Treatment;
1 - Treatment on Inner Face;
2 - Treatment on Outer Face;
3 - Treatment on both Sides.